

PRODUCT DESCRIPTION

A Classical long oil alkyd based interior high gloss coating for those high traffic and interior areas that need a highly washable coating in a wide range of colours.

PRODUCT FEATURES

- Highly washable, cleanable
- Excellent adhesion to range of properly prepared substrates
- Excellent, no mess application properties, with excellent, flow and levelling
- High hiding power and film build

APPLICATION AREAS

- Primed Plaster, Hardboard and Fibre cement walls
- Primed metal and wooden substrates

SURFACE PREPARATION

- Rusted Metal:** Affected areas need to be cleaned back to bright metal and spot primed with Heritage Water Based Metal primer.
- New Metal:** Surfaces need to be abrasively degreased to remove the manufacturer's grease protective layer this process is repeated until the surface is water break free. After drying the whole substrate is coated with Heritage Water Based Metal primer
- Dry uncoated concrete surfaces:** Remove all dust, foreign material, Fungal, algae growth- fill and seal all visible cracks and coat with Heritage Masonry primer
- Uncoated weathered or new fibre cement surfaces:** Remove dust, foreign material, Fungal, Algae growth and if friable, powdery seal with Heritage Masonry Primer
- Raw Plaster:** Remove all dust, foreign material, Fungal and Algae growth. Fill all visible cracks and coat with Heritage Masonry Primer
- Previously Painted Surfaces:** Remove all loose, flaking and bubbling paint. Remove all dust, grease, foreign material, Fungus and Algae growth. Allow to dry, if then powdery or friable seal with Heritage Masonry Primer. After drying over night all primed areas and previously areas must then be undercoated With Heritage Universal Undercoat for all surfaces.

APPLICATION PROCEDURE

- Stir well before use
- Brush, Mohair roller or airless spray (thin for spray 20% with Mineral turpentine) apply a generous coat of Heritage Economic Gloss Enamel to the area, which needs protecting.
- Allow to dry 18-24hours before recoating.
- Brush, roller or airless spray apply a second generous coat.
- Clean up application equipment with Mineral turpentine or Heritage Brush Cleaner/Degreaser

GENERAL

- Do not apply before 9am and after 4 pm in the Winter
- Heritage High Gloss enamel is ready for use un-thinned, thinning will reduce its hiding power
- Two coats of Heritage Economic Gloss Enamel are used for best results.
- Although the spreading rate will vary with porosity and type of substrate. For uncoated new work on 8-10 SQM/l for the first coat and 10-12 SQM/l for subsequent coats and for when applied to sealed, previously painted substrates
- Application equipment clean up is with Mineral turpentine/Heritage Brush cleaner degreaser

COLOUR RANGE/QUANTITIES

- Heritage High Gloss enamel is available in a range of popular ready mixed colours and on the Heritage Tinting system
- Available in 1/5/20 litres

PRECAUTIONS

- This material is highly flammable and has a flashpoint of 37 deg C
- Use only in well ventilated areas and do not eat, drink or smoke during application



LEAVE A LASTING IMPRESSION



info@heritagepaints.co.za

www.heritagepaints.co.za | 0800 0 PAINT - 0800 0 72468

Heritage Paints C.C. 18 Garland Street, Ophirton, Johannesburg